Test report	Report enquiry telephone: 0571-82327572 82327571 Report inquiry email: info@european-norm.com Report Query website: www.european-norm.com
Report number: ENT2511243718-y Security code	Page 1 of 3

QR REMOVED IN SAMPLE

Customer information	Applicant: Production Unit		
Customer sample information	Sample name: Width:0.7*10M		
Detection type	Commissioned inspection	Detection site	This laboratory
Description of the sample submitted	—	Sample status	No obvious abnormality
Sample acceptance/testing start date	2025/11/28	Report date	2025/11/29
Test/judgment basis	GB/T17591-2025 Flame retardant fabrics		
Comprehensive test conclusion	The tested and required items of the sample comply with the corresponding technical requirements of <GB/T17591-2025 Class B1>		
Test result and single decision	Individual results are detailed on the Detection data page. (Special stamp for inspection and testing)		
Sample presentation	The photo presentation of the sample and/or the paste sample cut from the submitted sample can be found on the last page of this report		
remark	The inspection and testing items in this report are carried out under the environmental conditions specified in the corresponding standards (except where indicated).		

欧标检测技术（杭州）有限公司 检验检测专用章

Authorized signatory:

(Physical items) (Chemical items)

Test report	Report enquiry telephone: 0571-82327572 82327571 Report inquiry email: info@european-norm.com Report Query website: www.european-norm.com
Report number: ENT2511243718-y Security code	Page 2 of 3

QR REMOVED IN SAMPLE

Test data:

Test item			unit	Test requirement	Test result	Single decision	Method standard
Flame Resistance	After flame Time	Warp	s	≤5	0	Conform to	GB/T5455-2014 condition A
		Weft	s	≤5	0	Conform to	GB/T5455-2014 condition A
	Smoldering Time	Warp	s	≤5	0	Conform to	GB/T5455-2014 condition A
		Weft	s	≤5	0	Conform to	GB/T5455-2014 condition A
	Damaged length	Warp	mm	≤150	23	Conform to	GB/T5455-2014 condition A
		Weft	mm	≤150	24	Conform to	GB/T5455-2014 condition A
	Burning drips		—	Did not cause the degreased cotton to burn or smolder	No dripping, will not cause the degreased cotton to burn or smoldering.	Conform to	GB/T5455-2014 condition A

Test report	Report enquiry telephone: 0571-82327572 82327571 Report inquiry email: info@european-norm.com Report Query website: www.european-norm.com
Report number: ENT2511243718-y Security code	Page 3 of 3

QR REMOVED IN SAMPLE

Sample for Testing

SAMPLE IMAGE WITHHELD

ENT2511243718

Statement:
1. This report may not be copied (except for full text copying) without the approval of this institution. Copies of the report without the special seal of this institution for inspection and testing ar
e invalid.
2. The report is invalid without the signature of the Approver (Authorized signatory); the report is invalid without the special seal of this institution for inspection and testing; the report is invalid if it has been altered.
3. The authenticity of the customer information and sample information provided by the client in the report is the responsibility of the client. The test results in the report are only responsible for the samples submitted for testing.
4. “*” indicates that the item is not within the scope of CNAS accreditation of this company. “#” indicates that the item was completed by a subcontracting laboratory.
5. If there are any objections to the test report, they should be raised to the testing unit within 15 days from the date of receipt of the report. Objections raised after this period will not be accepted.
6. The testing/evaluation basis is provided by the client, and the laboratory makes the determination at the client's request.

********** End of report **********